

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Patent Abstracts of Japan

PUBLICATION NUMBER : 55080479
PUBLICATION DATE : 17-06-80



APPLICATION DATE : 12-12-78
APPLICATION NUMBER : 53152628

APPLICANT : SANYO KOKUSAKU PULP CO LTD;

INVENTOR : AKIMOTO SABURO;

INT.CL : C09J 7/02

TITLE : MANUFACTURING OF
PRESSURE-SENSITIVE TYPE
ADHESIVE TAPE OR SHEET



ABSTRACT : PURPOSE: To manufacture a pressure sensitive adhesive tape or sheet which is excellent in adhesiveness to and releasability from base material by forming a pressure-sensitive adhesive layer composed primarily of a polyacrylate on the surface in contact with a releasable layer composed of a specific polyolefine elastomer and polyethylene.

CONSTITUTION: On the surface of the adhesive tape base (I) or the release sheet base (II), a mixture of a polyolefine elastomer, having a shear modulus (by JIS- 7213) of 2.0×10^8 dyne/cm² or less and an equilibrium contact angle of 55° or more under measuring conditions of a temperature of $20 \pm 1^\circ\text{C}$ and a relative humidity of $65 \pm 5\%$ for a standard liquid whose surface characteristic is a surface tension of 50dyne/cm (by JISK-6768) and a polyethylene, having an average molecular weight of 10,000 or more and a density of 0.91~0.97g/cm², is coated in a thickness of 1 micron or more to form the release layer (V), and then the pressure sensitive adhesive layer (IV) composed primarily of a polyacrylate is formed on the surface of the layer (V).

COPYRIGHT: (C) JPO